Effects of Graphene Supports on Palladium Catalyzed Reactions

Kathleen Dreyer

Herbert Wertheim College of Engineering, University of Florida

Faculty mentor: David Hibbitts, Department of Chemical Engineering

Abstract

Palladium (Pd) catalysts are often anchored to a support, such as graphitic carbon, to increase their overall surface area and facilitate catalytic reactions. There is a potential for interaction between the support and the catalyst, which can affect such reactions. It was hypothesized that electronic metal-support interactions between functionalized graphene supports and Pd particles affect the catalytic activity of the metal atoms, but such interactions are screened by the metal and become negligible at a certain size threshold of Pd. To determine this threshold, the Pd catalyst size and shape were varied (size was varied in the number of layers and number of Pd atoms, while shape ranged from hemispherical to spherical). The Pd clusters ranged from 2-5 layers and 38-293 atoms. Also, the graphene support was functionalized to different extents to test its electronic effects on catalytic reactions on Pd. Initially, adsorption reactions of small model adsorbates (H^* , O^* , C^* , OH^* , and CH^*) onto supported Pd were tested to determine the effects of catalyst shape and size on the binding energy of such species. Periodic density functional theory calculations were used to determine these binding energies on bare Pd, Pd on a pristine graphene support, and Pd on graphene functionalized with oxygen and hydroxide. These tests revealed that smaller Pd particles (~ 100 atoms) are influenced by the support, showing shifts in adsorbate binding energy of ~ 50 kJ mol^{-1} from the pure graphene to the functionalized graphene. This shift in binding energy indicates that there are major changes in the catalytic behavior of sites upon which the adsorption reaction was tested, meaning that sites near the Pd-graphene interface might be affected by the support.

Introduction

There are a number of benefits to supporting a catalyst on a porous material in catalytic reactions. It is often beneficial to heterogenize a homogeneous catalyst to make it easier to separate from reactants and products, which can be accomplished by affixing the catalyst particles to a support [1-2]. Utilizing a catalyst support can also hinder the agglomeration of catalyst particles, which is unfavorable for reactions [1, 3-5]. Because catalyst activity occurs on surface atoms, maximizing the surface area to volume ratio of catalyst particles by distributing them across a porous support can facilitate interactions with reacting species. Additionally, the porous nature of a catalyst support can make the catalyst more accessible to reactant phases [1,

5-7]. The addition of a catalyst support can also tune performance of a catalyst via charge density transfer between the metal and the support [4]. Attempts have been made to utilize charge transfer effects between oxide supports and metals, but charge transfer in carbon supports is virtually unexplored due to the complex nature of their chemistry [4, 6-8].

The following theoretical evidence serves to demonstrate that the functionalization of model carbon supports affects their interaction with palladium catalyst particles, thereby altering the activity of the palladium. Periodic density functional theory (DFT) calculations are used to establish a relationship between the functionalization of the carbon support, the charge distribution at the interface between the support and the catalyst, and the activity of the catalyst.

Methodology

Building Palladium Particles and Designing Carbon Supports

Palladium particles were modeled as cubo-octahedral particles, which are composed of (100) and (111) surfaces. The dimensions of the catalyst particles were modified to create sixteen structures of various shapes and sizes. The particles ranged in size from 38 to 293 Pd atoms and 2-5 metal layers (orthogonal to the carbon support), and ranged in shape from hemispherical to spherical. Figure 1 shows examples of two particles, one with two Pd layers and one with four-layers.

Figure 1. Top and side view of a two layer Pd particle (a, c) and a four layer Pd particle (b, d).

The carbon support was modeled as various forms of graphene, which consists of a sheet of sp^2 hybridized carbons arranged in six-membered rings. The support was either a single-layer graphene sheet, a two-layer graphene sheet, or a functionalized graphene sheet. Two functionalized graphene sheets were modeled: a high coverage graphene sheet (which has

0.125ML of O* and 0.125ML of OH* adsorbed) and a low coverage graphene sheet (which has 0.125ML of O* and 0.125ML of OH* adsorbed). Examples of a pure graphene support and a high coverage functionalized graphene support are presented in Figure 2.

Figure 2. Pure graphene support (a) and high coverage functionalized graphene support, with functional groups pointing downward (b)

The lattice parameters for the the high coverage functionalized graphene sheet increased to 8.702 and 2.512 from 8.523 and 2.46 for an equivalent pure graphene sheet, indicating that functionalization of the graphene sheet is associated with an expansion in C–C bonds. Additionally, both functionalized graphene sheets are curved in a periodic manner, which enables C–C bond expansion in a way that corresponds with the rehybridization of carbon atoms from sp^2 to sp^3 .

Modelling Reactions on Pd Particles

Adsorption reactions of various atoms and molecules were initially examined to gain insight into how reaction energies differed on the modelled supports. Probe adsorbates H*, O*, C*, OH*, and CH* were modeled on the Pd particles at sites far from the Pd–support interface to differentiate any observed effects from direct interfacial interactions. Adsorbates were positioned on the (111) surface opposite from the Pd–support interface, at a three-fold face-centered cubic (FCC) site in the center of the particle. Figure 3 exemplifies the positioning of adsorbates on the Pd particles.

Figure 3. O* adsorbed to the top of a Pd particle on pure

Adsorption reactions were modelled as taking the adsorbate from infinitely far away and adsorbing it to the palladium. As such, each palladium-support structure was modelled and optimized as a stand-alone structure, as were each of the adsorbates (H* and O* were modelled as one half of an H₂ molecule and one half of an O₂ molecule, respectively). Plane-wave DFT calculations were performed to determine interaction energies between Pd particles and graphene supports and binding energies of probe adsorbates. Binding energies for each of the adsorbates were calculated using the following equation:

$$\text{BE} = \text{E}[\text{adsorbate on Pd on support}] - \text{E}[\text{Pd on support}] - \text{E}[\text{adsorbate}] \quad (1)$$

where BE denotes the binding energy of the respective adsorbate and E represents the energy of the respective species.

To compare binding energies between the pure graphene support and each functionalized support, an absolute change in binding energy was calculated using the following equation:

$$\Delta\text{BE} = |\text{E}[\text{adsorbate on Pd on functionalized support}] - \text{E}[\text{Pd on functionalized support}] - (\text{E}[\text{adsorbate on Pd on support}] - \text{E}[\text{Pd on support}])| \quad (2)$$

where ΔBE represents the absolute value of the change in binding energy of the adsorbate between pure and functionalized graphene and E represents the energy of the respective species.

Results

Initially the binding geometries of the palladium clusters were compared on the modelled graphene supports. In the case of the pure graphene sheets, the Pd merely physisorbs above the support. However, for both functionalized supports, the palladium chemisorbs to the support. An example of these binding geometries is shown in Figure 4. The exothermic interaction energies for palladium particles on pure graphene supports were all less than $5 \text{ kJ mol}^{-1} \text{ Pd}^{-1}$, whereas the exothermic interaction energies on the high coverage functionalized graphene were between 30 and $50 \text{ kJ mol}^{-1} \text{ Pd}^{-1}$, indicating a much stronger interaction between the Pd particles and the high coverage functionalized support.

Figure 4. Side view of binding geometry of Pd particle on pure graphene (a) and high coverage functionalized graphene (b)

The shifts in binding energies for probe adsorbates were compared next on the pure graphene support and the high coverage functionalized graphene support. The absolute shift in binding energy for each of the sixteen particles is shown in Figure 5.

Figure 5. Absolute change in binding energy of H* (blue), O* (red), C* (orange), CH* (green), and OH* (purple) between pure graphene and high coverage functionalized graphene

It is apparent from Figure 5 that as the number of layers in the Pd cluster increases, the magnitude of the shift in binding energy tends to decrease.

Adsorption reactions on the low coverage functionalized graphene were also studied, revealing similar trends to those on the high coverage support. Figure 6 shows the absolute shift in binding energy for each of the particles on the low coverage graphene.

Figure 6. Absolute change in binding energy of H* (blue), O* (red), C* (orange), CH* (green), and OH* (purple) between pure graphene and d low coverage functionalized graphene

Conclusions

The binding geometries and interaction energies of the palladium clusters on the modelled supports demonstrate that the electronic metal-support interactions vary depending on the extent to which the support is functionalized. Additionally, the binding energy shifts shown in Figures 5 and 6 further prove that functionalization of the graphene support alters the palladium-support interactions. The addition of electron-withdrawing groups to the carbon support induces charge transfer from the metal to the graphene, which results in the aforementioned binding energy shifts. As particle size increases, the magnitude of the shift decreases, suggesting that atoms close to the metal-support interface are significantly altered by the support, and that the effects may depend on the surface chemistry, i.e. functionalization, of the carbon support.

This study served to elucidate the influence of graphene support functionalization on electronic properties of the metal catalyst, which was previously unknown for carbon supports. Improving the understanding of how carbon supports interact with Pd provides insights into how these supports can be designed to optimize catalytic performance. Along with catalyst shape,

size, and coverage, it is apparent that support functionalization can, too, be utilized to enable efficient, logical design of carbon-supported Pd catalysts.

References

- [1] Julkapli, Nurhidayatullaili M., and Samira Bagheri. "Graphene supported heterogeneous catalysts: An overview." *Int J Hydrogen Energ*, vol. 40, no. 2, 2015.
- [2] Copéret, C., Chabanas, M., Petroff Saint-Arroman, R. & Basset, J.-M. "Homogeneous and heterogeneous catalysis: Bridging the gap through surface organometallic chemistry." *Angew Chem Int Ed*, vol. 42, 156–181, 2003.
- [3] Zhou, Xuejun, et al. "A Review of Graphene-Based Nanostructural Materials for Both Catalyst Supports and Metal-Free Catalysts in PEM Fuel Cell Oxygen Reduction Reactions." *Adv Energy Mater*, vol. 4, no. 8, 2014.
- [4] Rao, Radhika G., et al. "Interfacial charge distributions in carbon-supported palladium catalysts." *Nat Commun*, vol. 8, no. 340, 2017.
- [5] Hur, Seung H., and Jin-Nam Park. "Graphene and its application in fuel cell catalysis: a review." *Asia-Pac J Chem Eng*, vol. 8, no. 2, 2012.
- [6] Matsubu, J. C. et al. "Adsorbate-mediated strong metal–support interactions in oxide-supported Rh catalysts." *Nat Chem*, vol. 9, 120–127, 2016.
- [7] Willinger, M. G. et al. "A case of strong metal–support interactions: combining advanced microscopy and model systems to elucidate the atomic structure of interfaces." *Angew Chem Int Ed*, vol. 53, 5998–6001, 2014.
- [8] Tauster, S. J. "Strong metal-support interactions." *Acc Chem Res*, vol. 20, 389–394, 1987.